

TEST CERTIFICATE

BT-20-07-22-01

Client: SWISS KRONO sp. z o.o.
ul. Serbska 56, 68-200 Żary, Poland

Product:

- SWISS KRONO Laminated MDF flameproof Stop Fire
- SWISS KRONO Laminated MDF
- SWISS KRONO Laminated Particleboard flameproof Stop Fire
- SWISS KRONO Laminated Particleboard

Order: Determination of the antibacterial properties of surfaces

Test standard: ISO 22196 (2011): Plastics – Measurement of the antibacterial activity on plastics surfaces.

Test report: no. 2220033 (07/07/2020)

Results:

	Decimal logarithm of the number of viable bacteria after the incubation time of 24 hours [CFU/cm ²]	
	<i>Staphylococcus aureus</i> DSM 799	<i>Escherichia coli</i> DSM 1576
Reference material	U _{T_Sa} = 3.4	U _{T_Ec} = 3.2
Laminated board SWISS KRONO	A _{T_Sa} < 1.4	A _{T_Ec} < 1.1
Antibacterial activity*: R = U – A		
Laminated board SWISS KRONO	R_{Sa} > 2.0	R_{Ec} > 2.1

*) A clear antibacterial activity is given if R ≥ 1.0 at both bacteria strains.

The test material is classified as “antibacterial”.

Dresden, 22/07/2020



Head of laboratory




Engineer in charge